

ALPHA-1 FLUID

Planet Saving Solutions

- Factory Mutual
RECOMMENDED
- High dielectric strength
- Excellent fire safety rating
- Highly efficient cooling properties
- Superior oxidation and stability resistance
- Fluid of choice for original fill or retrofit

Synthetic Fire Resistant Dielectric Fluid for Original or Retrofill of Power Transformers

Alpha-1 Fluid is a fire-resistant dielectric fluid that is unmatched in its ability to cool transformers. Made with synthetic hydrocarbon oils, it has the best heat transfer and low-temperature properties available. Its cooling characteristics make it an excellent choice for original equipment fill and the industry standard for retro-filling mineral oil transformers to upgrade fire safety. Request DSI's Retro-fill guide for further assistance and recommendations.

Due to its lower viscosity, Alpha-1 Fluid flows more easily, thereby cooling your equipment better. Alpha-1 Fluid has outstanding oxidation stability at high temperatures. Alpha-1 Fluid is compatible with conventional transformer oil and other insulating fluids (note: Alpha-1 is not compatible with silicone fluid)



As an FM recommended fluid, please refer to www.fmglobal.com to review supporting articles on how to receive potential cost breaks by using Alpha-1 Fluid in your business.



1320 E. Commerce St.
Tyler, TX 75702
800-796-0220
sales@dsiventures.com

DSIventures.com

Applications

- Any dielectric application where the risk of fire must be minimized
- Excels where operating temperatures need to be controlled such as power and distribution transformers, transformer-rectifier sets, load-break and tap-changers
- Chosen for use in extreme high/low temperature applications, viscosity-dampened switchgears and overloaded transformers
- Exceptional heat transfer characteristics ensures equipment maintains low operating temperature

TYPICAL CHARACTERISTICS - Compared with ASTM D5222, Guide for High Fire point Oils

<i>Characteristic & ASTM method</i>	<i>Alpha-1</i>	<i>ASTM Spec</i>
Fire Point, D92, °C.	308	145
Viscosity, D88, cSt. @ 100 °C.	9.3	11.5-14.5
Density @ 20 °C, g/cc	0.83	0.86
Pour Point, D97, °C.	-54	-40
Color, ASTM units	L0.5	L1.5
Appearance	Clear	clear
Dielectric Breakdown, D1816, kV	58	56
Dissipation Factor, 100 °C, D924, %	0.01	0.30
Acid Value, D664, mg KOH/g	0.01	0.02